



**GRAUER & WEIL (INDIA) LTD.**  
**Unit : Bombay Paints**



## **BPL MARINE ANTICORROSIVE PRIMER.**

**DESCRIPTION** **BPL MARINE ANTICORROSIVE PRIMER** paint is an aluminum pigmented phonemic bituminous paint.

**TYPICAL** As an intermediate coat between BPL MARINE UNDERWATER PRIMER & ANTIFOULING.

### **PRODUCT DATA**

<b>APPLICATION</b>	Airless Spray, Air Spray and Brush
<b>NOZZLE ORIFICE</b>	0.018 "
<b>NOZZLE PRESSURE</b>	2175 psi
<b>VOLUME SOLIDS</b>	54.0%
<b>RECOMMENDED DFT</b>	30 microns
<b>CORRESPONDING WFT</b>	75 microns
<b>THEORETICAL SPREADING RATE AT ABOVE DFT</b>	18 M <sup>2</sup> / Ltr
<b>DRYING - SURFACE DRY</b>	4-5 hrs
<b>COLOUR</b>	BROWN
<b>FINISH</b>	Semi matt
<b>OVERRATING INTERVAL</b>	min 4 hrs, max. None
<b>THINNER</b>	108
<b>FLASH POINT</b>	25° C
<b>SHELF LIFE</b>	12 months
<b>PRECEDING COAT</b>	BPL MARINE UNDERWATER PRIMER
<b>APPLICATION CONDITIONS</b>	As dictated by good painting practice

**M-1-C.**

## **:: 2 :: BPL MARINE ANTICORROSIVE PAINT**

SUBSEQUENT COATS

BPL MARINE System according to specification

SAFETY

As a general rule, avoid inhalation of solvent vapour or paint mist and contact of liquid paint with skin and eyes. Provide forced ventilation when working with solvent borne coating in confined spaces or stagnant air. Provide respiratory, skin & eye protection. Follow local and national safety regulations.

**ISSUED**

**JANUARY 2007.**

**M-1-C.**