



BPL MARINE PRIMER

DESCRIPTION

BPL MARINE PRIMER is an Anticorrosive primer based on Anticorrosive pigment.

TYPICAL USE

As a general purpose primer on exterior and interior steel in mild to moderately corrosive environment. Not recommended for immersion services.

PRODUCT DATA

APPLICATION

Airless Spray, Air Spray or Brush

FINISH

Semi Matt

NOZZLE ORIFICE

0.018"

NOZZLE PRESSURE

2200 psi

VOLUME SOLIDS

44%

RECOMMENDED DFT

40 microns

CORRESPONDING WFT

100 microns

THEORETICAL SPREADING RATE AT ABOVE DFT

11 sq.mtrs/Ltr

DRYING-SURFACE DRY

3-4 hrs

COLOUR

RED / GREEN

OVERCOAT INTERVAL

Min 16 hrs, max none

SURFACE PREPARATION

NEW STEEL: Abrasive blasting to Sa 2½ For repair & touch-up use BPL MARINE PRIMER.

SUBSEQUENT COAT

BPL MARINE SYNTHETIC ENAMEL OR BPL MARINE BD COATING.

SAFETY

As a general rule, avoid inhalation of solvent vapors or paint mist and contact of liquid paint with skin and eyes. Provide forced ventilation when working with solvent borne coating in confined spaces or stagnant air. Provide respiratory, skin & eye protection. Follow local and national safety regulations.

ISSUED

JANUARY 2007.

M-1-A.