



BPL MARINE SYNTHETIC ENAMEL

DESCRIPTION

BPL MARINE SYNTHETIC ENAMEL is an alkyd based paint which has good weather resistance, good gloss and colour retention.

TYPICAL USE

1. Performs as a finishing coat on exterior and wood work etc in mild to moderately corrosive environment.
2. As a finishing coat in engine rooms including main engine and auxiliary equipments
3. As a finishing on tank tops in engine rooms and similar areas.

PRODUCT DATA-

APPLICATION	Airless Spray, Air Spray or Brush
NOZZLE ORIFICE	0.018"
NOZZLE PRESSURE	2175 psi
VOLUME SOLIDS	35%
RECOMMENDED DFT	30 microns
CORRESPONDING WFT	100 microns
THEORETICAL SPREADING RATE AT ABOVE DFT	11.6 M ² / Ltr
DRYING TIME-SURFACE DRY	3-4 hrs
COLOUR	White & assorted colours
FINISH	Glossy
FLASH POINT	30° C
SHELF LIFE	1 year

:: 2 :: BPL MARINE SYNTHETIC ENAMEL

RECOATING INTERVAL	Min 8 hrs, Max.None
APPLICATION CONDITIONS	As dictated by good painting practice
RECOATING INTERVAL	Min 8 hrs, Max.None
APPLICATION CONDITIONS	As dictated by good painting practice
PROCEEDING COAT	BPL MARINE PRIMER, BPL MARINE UNDERCOATING.
SAFETY	As a general rule, avoid inhalation of solvent vapour or paint mist and contact of liquid paint with skin and eyes. Provide forced ventilation when working with solvent borne coatings in confined spaces or stagnant air. Provide respiratory, skin & eye protection. Follow local and national safety regulations.

ISSUE

JANUARY 2007.